

# Material data sheet

Insulating strips of PA 66 GF25,  
dry impact resistant

## PA 66 GF25, dry impact resistant

Characteristic	Reference standard	Unit	Samples from extruded insulating strips		Samples from injection molding
			Dry <sup>(1)</sup>	Equilibrium moisture content <sup>(2)</sup>	Dry <sup>(1)</sup>
Melting temperature	EN ISO 11357-3	°C	≥ 250 <sup>(3)</sup>	≥ 250 <sup>(3)</sup>	≥ 250 <sup>(3)</sup>
Density	EN ISO 1183-1 or -3	g/cm <sup>3</sup>	1.3 +/- 0.05	1.3 +/- 0.05	1.3 +/- 0.05
Annealing residue (glass fibre content)	EN ISO 1172	%	25 +/- 2.5	25 +/- 2.5	25 +/- 2.5
Tensile strength	EN ISO 527-2	N/mm <sup>2</sup>	≥ 80 <sup>(4)</sup>	≥ 50 <sup>(4)</sup>	≥ 110 <sup>(5)</sup>
Young's modulus	EN ISO 527-2	N/mm <sup>2</sup>	≥ 4500 <sup>(4)</sup>	≥ 2000 <sup>(4)</sup>	≥ 6000 <sup>(5)</sup>
Elongation at break	EN ISO 527-2	%	≥ 3 <sup>(4)</sup>	≥ 7 <sup>(4)</sup>	≥ 3 <sup>(5)</sup>
Thermal conductivity	EN 12664	W/mK		0.30 <sup>(6)</sup>	
Reaction to fire	EN 13501-1	-		class E <sup>(7)</sup>	

TBGroup-Do-TPI-14\_V7\_02.2025

**Material is suitable to be used as thermal barrier with mechanical functions according to EN 14024<sup>(8)</sup>**

- 1) Sample water content less than 0.2 % by weight
- 2) Fast conditioning acc. to EN ISO 1110
- 3) Maximum temperature 300 °C
- 4) Specimen Type 1BA - mean value with minimum sample size of 5 specimens at room temperature - tension measured in extrusion direction
- 5) Specimen Type 1A
- 6) The declared value is taken from ISO 10077-2 and can be used for thermal performance of frames according to the mentioned standard
- 7) Report 24-003934-PR02
- 8) EN14024:2004 chapter 4.2 Report 12-001212-PR09 ift Rosenheim GmbH (corresponds to EN14024:2023 ch. 5.2 parts a, b, c, d and f)

**In case of specific questions we gladly offer you our individual support**

**Insulation solutions for  
windows, doors, and facades**